

## Abstract

Using molecular-dynamics simulation coupled with an analysis of equilibrium capillary fluctuations in interfacial position, we compute the magnitude and anisotropy of the interfacial free energy for a binary hard-sphere system with a diameter ratio  $\gamma = 0.9$ . This system, in which the fluid mixture coexists with a randomly substituted face-centered-cubic solid solution, is a useful reference model for alloys. Our results show that  $\gamma$  increases with increasing mole fraction of the smaller sized particle when temperature is held constant. However, after rescaling the results to fixed pressure and varying temperature, we find that  $\gamma$  decreases with increased alloying by the smaller particle (corresponding to lower temperatures). Thus,  $\gamma$  is seen to decrease with increasing concentration of the lower melting point solute, consistent with earlier simulations on Ni/Cu and Lennard-Jones mixtures. The anisotropy in  $\gamma$  is such that the inequality  $\gamma_{100} > \gamma_{110} > \gamma_{111}$  holds for all concentrations studied. Using the classification scheme of Haxhimali *et al.*, [Nat. Mater. **5**, 660 (2006)] we find that the anisotropy in  $\gamma$  is consistent with a predicted  $\langle 100 \rangle$  primary dendrite growth direction.